

**CERISIE**

LABORATORIO ITALIANO GOMMA



Date, March 07th, 2018
 TR n° **530-(eng)/2017**
 Ref. Your Confirm dated 12.09.2017

To

TUBI GOMMA TORINO S.p.A.

Strada Statale 31, Km 39,4 n.42

15040 MIRABELLO MONFERRATO (AL)

Received 14.09.2017

Start tests 18.09.2017

End tests 23.10.2017

Page 1 of 2

SUPPLEMENT TO TEST REPORT

Subject: SUITABILITY TO BE USED IN CONTACT WITH FOODS, ACCORDING TO DM 21.03.73 and Subsequent Amendments AND TO RULE 1935/2004/CE and Subsequent Amendments, ON A RUBBER COMPOUND MARKED "BIIR ST BIANCO FDA" SUPPLIED AS VULCANIZED RUBBER SHEETS 2 mm thick

RUBBER COMPOUND
 (Rubber Sheets 200x200x2 mm)

BIIR ST BIANCO FDA**Test method**

Requirements
 DM 21/03/73
 DM 26/04/93 N. 220
 DM 24/09/96
 N.572

TESTS CONDITIONSSimulators of food

B
 Acetic acid 3% (p/v)
 in water solution

 Ethanol 96% (v/v) in
 water solution

DM 22/07/98
 N.338
 Annex Chap. I
 DM 24/09/96
 N.572

.....

Time and temperature of contact

4 h at 100°C

4 h at 100°C

DM 22/07/98
 N.338
 Annex Chap. II

.....

TESTSTotal migration

mg/kg

27,0

23,3

DM 26/04/93
 N. 220 All. III
 Sec. 1/B

≤ 50

Specific Migration of thiuram

mg/kg

Not revealable
 (< 0,002)

0,03

DM 21/03/73
 Ann.IV Sec. 3.1

≤ 1

Date, March 07th, 2018

TR n° 530-(eng)/2017 Page 2 of 2



SUPPLEMENT TO TEST REPORT


REMARK:

The test are conducted on rubber sheets of vulcanized rubber, applying the criteria set forth in Article 4, the DM 18.06.1979 Point 4 as the material is intended for the production of different types of product.

On the basis of the test results and on the basis of the recipe provided by the Customer, **we certifies** that the examined rubber compound marked "**BIIR ST BIANCO FDA**" **is in compliance:**

- for the contact with **acid foods, and alcoholic foods at any alcohol content** according to the **Requirements of DM 21.03.73 and Subsequent Amendments** in any condition of time and temperature r **when** in the space of **1 hour, 1 dm² of rubber compound comes into contact with at least 2 kg of food.**

L'OPERATORE



E. Badomer

IL DIRETTORE


F. Negroni